

Permeation breakthrough times according to EN374-3:2003 (minutes)

Glove :

Solvex® 37-900

	Chemical Agent	Breakthrough Time	Protection Index	CAS Number	Notified Body	EN Standard
	1,2-dichloroethane	9.5	0	107-06-2	Centexbel	374-3:1994
	1,2-propylene oxide	4	0		Force Technology	374-3:1994
	1-Methoxy-2-Propanol	318	5	107-98-2	Centexbel	374-3:2003
	1-Methoxy-2-propylacetate	203	4	108-65-6	Force Technology	374-3:2003
	1-Methyl-2-butylacetate	173	4		Centexbel	374-3:2003
	3-bromo-1-propene	7.5	0		Force Technology	374-3:2003
	Acetic Acid, Glacial	103	3	64-19-7	Centexbel	374-3:2003
	Acetone	7	0	67-64-1	Centexbel	374-3:2003
	Acetonitrile	14	1	75-05-8	Centexbel	374-3:2003
	Acrylic Acid	35	2	79-10-7	Centexbel	374-3:2003
	Acrylonitrile	8	0	107-13-1	Force Technology	374-3:2003
	Allyl-2,3-epoxypropylether	22	1		Force Technology	374-3:2003
	Ammonium Hydroxide, 25%	311	5	1336-21-6	Centexbel	374-3:2003
	Benzene	26	1	71-43-2	Centexbel	374-3:2003
	Benzine (FAM DIN 51635)	> 480	6		Centexbel	374-3:2003
	Bromine	29	1		Centexbel	374-3:2003
	Butyl Acetate	44	2	123-86-4	Centexbel	374-3:2003
	Carbon disulfide	12	1	75-15-0	Centexbel	374-3:2003
	Cyclohexane	> 480	6	110-82-7	Centexbel	374-3:2003

Permeation breakthrough times according to EN374-3:2003 (minutes)

0	1	2	3	4	5	6
< 10	10-30	30-60	60-120	120-240	240-480	> 480
Not recommended	Splash protection		Medium protection		High protection	

Data given in the table above are based on results of laboratory tests performed on the palm area of the glove or are based on extrapolations from the results of laboratory tests. These tests were run using standard test methods that may not adequately replicate any specific conditions of end use. Because Ansell has no detailed knowledge or control over the conditions of end use, any of these data must be advisory only, and Ansell must decline any liability.

Ansell Healthcare Europe N.V. (European Head Office)

Riverside Business Park, Block J

Boulevard International 55, 1070 Brussels, Belgium

Tel. +32 (0) 2 528 74 00 • Fax +32 (0) 2 528 74 01 • Fax Customer Service +32 (0) 2 528 74 03

<http://www.ansell.eu> • E-mail info@ansell.eu



Permeation breakthrough times according to EN374-3:2003 (minutes)

Glove :

Solvex® 37-900

	Chemical Agent	Breakthrough Time	Protection Index	CAS Number	Notified Body	EN Standard
	Cyclohexanone	58	2	108-94-1	Centexbel	374-3:2003
	Diethyl ether	59	2	60-29-7	Centexbel	374-3:2003
	Diethylamine	26	1	109-89-7	Centexbel	374-3:2003
	Diethylene glycol dimethyl ether	29	1		Force Technology	374-3:2003
	Dimethylacetamide	24	1	127-19-5	Centexbel	374-3:2003
	Dimethylformamide	20	1	68-12-2	Centexbel	374-3:2003
	Epichlorohydrine	12	1	106-89-8	Force Technology	374-3:2003
	Ethanol, 95%	325	5	64-17-5	Centexbel	374-3:2003
	Ethyl Acetate	18	1	141-78-6	Centexbel	374-3:2003
	Ethylamine	87	3	75-04-7	Centexbel	374-3:2003
	Formic acid, 98-100%	46	2	64-18-6	Force Technology	374-3:2003
	Heptane	> 480	6	142-82-5	Centexbel	374-3:2003
	Hydrofluoric Acid, 60%	24	1	7664-39-3	Force Technology	374-3:2003
	Hydrogen Peroxide, 30%	> 480	6	7722-84-1	Centexbel	374-3:2003
	Isophorone	249	5	78-59-1	Centexbel	374-3:2003
	Isopropanol	> 480	6	67-63-0	Centexbel	374-3:2003
	Methanol	74	3	67-56-1	Centexbel	374-3:2003
	Methyl Isobutyl Ketone	60	3	108-10-1	Centexbel	374-3:2003
	Methyl ethyl ketone	11	1	78-93-3	Centexbel	374-3:2003

Permeation breakthrough times according to EN374-3:2003 (minutes)

0	1	2	3	4	5	6
< 10	10-30	30-60	60-120	120-240	240-480	> 480
Not recommended	Splash protection		Medium protection		High protection	

Data given in the table above are based on results of laboratory tests performed on the palm area of the glove or are based on extrapolations from the results of laboratory tests. These tests were run using standard test methods that may not adequately replicate any specific conditions of end use. Because Ansell has no detailed knowledge or control over the conditions of end use, any of these data must be advisory only, and Ansell must decline any liability.

Ansell Healthcare Europe N.V. (European Head Office)

Riverside Business Park, Block J

Boulevard International 55, 1070 Brussels, Belgium

Tel. +32 (0) 2 528 74 00 • Fax +32 (0) 2 528 74 01 • Fax Customer Service +32 (0) 2 528 74 03

<http://www.ansell.eu> • E-mail info@ansell.eu



Permeation breakthrough times according to EN374-3:2003 (minutes)

Glove :

Solvex® 37-900

	Chemical Agent	Breakthrough Time	Protection Index	CAS Number	Notified Body	EN Standard
	Methyl-t-butyl Ether	> 480	6	1634-04-4	Centexbel	374-3:2003
	Methylenechloride	4	0	75-09-2	Centexbel	374-3:2003
	Methylmethacrylate	29	1	80-62-6	Centexbel	374-3:2003
	N-methyl-2-pyrrolidone	27	1	872-50-4	Centexbel	374-3:2003
	Nitric Acid, 70%	41	2	7697-37-2	Centexbel	374-3:2003
	Nitrobenzene	148	4	98-95-3	Centexbel	374-3:2003
	Perchloric Acid, 70%	> 480	6	7601-90-3	Centexbel	374-3:2003
	Perchloroethylene	305	5	127-18-4	Centexbel	374-3:2003
	Phenol 90%	78	3	108-95-2	Force Technology	374-3:2003
	Propionitrile	14	1	107-12-0	Satra	374-3:2003
	Propylene Glycol	> 480	6	57-55-6	Force Technology	374-3:2003
	Pyridine	13	1	110-86-1	Centexbel	374-3:2003
	Sodium Hydroxide, 50%	> 480	6	1310-73-2	Centexbel	374-3:2003
	Styrene	22	1	100-42-5	Centexbel	374-3:2003
	Sulphuric acid, 95%	116	3	7664-93-9	Centexbel	374-3:2003
	Sulphuric acid, 96%	105	3	7664-93-9	Centexbel	374-3:2003
	Tetrahydrofuran	11	1	109-99-9	Centexbel	374-3:2003
	Tetrahydrothiophene	31	2	110-01-0	Centexbel	374-3:2003
	Toluene	34	2	108-88-3	Centexbel	374-3:2003

Permeation breakthrough times according to EN374-3:2003 (minutes)

0	1	2	3	4	5	6
< 10	10-30	30-60	60-120	120-240	240-480	> 480
Not recommended	Splash protection		Medium protection		High protection	

Data given in the table above are based on results of laboratory tests performed on the palm area of the glove or are based on extrapolations from the results of laboratory tests. These tests were run using standard test methods that may not adequately replicate any specific conditions of end use. Because Ansell has no detailed knowledge or control over the conditions of end use, any of these data must be advisory only, and Ansell must decline any liability.

Ansell Healthcare Europe N.V. (European Head Office)

Riverside Business Park, Block J

Boulevard International 55, 1070 Brussels, Belgium

Tel. +32 (0) 2 528 74 00 • Fax +32 (0) 2 528 74 01 • Fax Customer Service +32 (0) 2 528 74 03

<http://www.ansell.eu> • E-mail info@ansell.eu



Permeation breakthrough times according to EN374-3:2003 (minutes)

Glove :

Solvex® 37-900

	Chemical Agent	Breakthrough Time	Protection Index	CAS Number	Notified Body	EN Standard
	Triethylamine	> 480	6	121-44-8	Centexbel	374-3:2003
	Xylene	57	2	1330-20-7	Centexbel	374-3:2003
	n-Undecane	> 480	6	1120-21-4	Centexbel	374-3:2003

Permeation breakthrough times according to EN374-3:2003 (minutes)

0	1	2	3	4	5	6
< 10	10-30	30-60	60-120	120-240	240-480	> 480
Not recommended	Splash protection		Medium protection		High protection	

Data given in the table above are based on results of laboratory tests performed on the palm area of the glove or are based on extrapolations from the results of laboratory tests. These tests were run using standard test methods that may not adequately replicate any specific conditions of end use. Because Ansell has no detailed knowledge or control over the conditions of end use, any of these data must be advisory only, and Ansell must decline any liability.

Ansell Healthcare Europe N.V. (European Head Office)

Riverside Business Park, Block J

Boulevard International 55, 1070 Brussels, Belgium

Tel. +32 (0) 2 528 74 00 • Fax +32 (0) 2 528 74 01 • Fax Customer Service +32 (0) 2 528 74 03

<http://www.ansell.eu> • E-mail info@ansell.eu

