Permeation breakthrough times according to EN374-3:2003 (minutes)

Glove:

Solvex® 37-185

Chemical Agent	Breakthrough Time	Protection Index	CAS Number	Notified Body	EN Standard
Acetic Acid, Glacial	190	4	64-19-7	Centexbel	374-3:2003
Acetonitrile	20	1	75-05-8	Centexbel	374-3:2003
Benzene	32	2	71-43-2	Centexbel	374-3:2003
Carbon disulfide	< 5	0	75-15-0	Centexbel	374-3:2003
Cyclohexanone	113	3	108-94-1	Centexbel	374-3:2003
Diethylamine	48	2	109-89-7	Centexbel	374-3:2003
Dimethylformamide	43	2	68-12-2	Centexbel	374-3:2003
Ethylene Glycol	>480	6	107-21-1	Centexbel	374-3:2003
Freon TF	> 480	6	76-13-1	Centexbel	374-3:2003
Heptane	> 480	6	142-82-5	Centexbel	374-3:2003
Hexane	> 480	6	110-54-3	Centexbel	374-3:2003
Hydrochloric Acid, 37%	> 480	6	7647-01-0	Centexbel	374-3:2003
Methanol	170	4	67-56-1	Centexbel	374-3:2003
Nitrobenzene	305	5	98-95-3	Centexbel	374-3:2003
Perchloroethylene	397	5	127-18-4	Centexbel	374-3:2003
Sodium Hydroxide, 50%	> 480	6	1310-73-2	Centexbel	374-3:2003
Sulphuric acid, 96%	127	4	7664-93-9	Centexbel	374-3:2003
Tetrahydrothiophene	66	3	110-01-0	Centexbel	374-3:2003
Toluene	54	2	108-88-3	Centexbel	374-3:2003

Permeation breakthrough times according to EN374-3:2003 (minutes)							
0	1	2	3	4	5	6	
< 10	10-30	30-60	60-120	120-240	240-480	> 480	
Not recommended	Splash protection		Medium p	protection	High protection		

Data given in the table above are based on results of laboratory tests performed on the palm area of the glove or are based on extrapolations from the results of laboratory tests. These tests were run using standard test methods that may not adequately replicate any specific conditions of end use. Because Ansell has no detailed knowledge or control over the conditions of end use, any of these data must be advisory only, and Ansell must decline any liability.



Permeation breakthrough times according to EN374-3:2003 (minutes)

Glove:

Solvex® 37-185

	Chemical Agent	Breakthrough Time	Protection Index	CAS Number	Notified Body	EN Standard	
	Triethanolamine	> 480	6	102-71-6	Centexbel	374-3:2003	
	Xylene	98	3	1330-20-7	Centexbel	374-3:2003	

Permeation breakthrough times according to EN374-3:2003 (minutes)							
0	1	2	3	4	5	6	
< 10	10-30	30-60	60-120	120-240	240-480	> 480	
Not recommended	Splash protection		Medium p	protection	High protection		

Data given in the table above are based on results of laboratory tests performed on the palm area of the glove or are based on extrapolations from the results of laboratory tests. These tests were run using standard test methods that may not adequately replicate any specific conditions of end use. Because Ansell has no detailed knowledge or control over the conditions of end use, any of these data must be advisory only, and Ansell must decline any liability.

